



تجارت الکترونیک فارس اویسا

مشخصات فنی قیر امولسیوني کنگیر 2 CMS  
Bitumen Emulsion Grade CMS 2 (Medium)

| Item                                      | Min      | Max |
|---|----------|-----|
| Test on emulsions                         |          |     |
| Viscosity, Saybolt Furol at 50°C SFs:     | 50       | 450 |
| Storage stability test, 24-h, %A:         | -        | 1   |
| Particle charge test:                     | Positive |     |
| Sieve test, %A:                           | -        | 0.1 |
| Coating ability and water resistance      |          |     |
| Coating, dry aggregate:                   | Good     | -   |
| Coating, after spraying:                  | Fair     | -   |
| Coating, wet aggregate:                   | Fair     | -   |
| Coating, after spraying:                  | Fair     | -   |
| Distillation                              |          |     |
| Oil distillate, by volume of emulsion, %: | -        | 12  |
| Residue, %:                               | 65       | -   |
| Tests on residue from distillation test   |          |     |
| Penetration, 25°C, 100 g, 5 s:            | 100      | 250 |
| Ductility, 25°C, 5 cm/min, cm:            | 40       | -   |
| Solubility in trichloroethylene, %:       | 97.5     | -   |

*AVLS*



تجارت الکترونیک فارس اویسا  
شماره ثبت : ۴۷۱۲۲۴