

مشخصات فنی قیر امولسیوني زودگیر 1 CRS

Bitumen Emulsion Grade CRS 1 (Rapid)

Item	Min	Max
Test on emulsions		
Viscosity, Saybolt Furol at 50°C SFs:	20	100
Storage stability test, 24-h, %A:	-	1
Demulsibility, 35 mL, 0.8 % dioctyl sodium:	40	-
Particle charge test:	Positive	
Sieve test, %A:	-	0.1
Distillation		
Oil distillate, by volume of emulsion, %:	-	3
Residue, %:	60	-
Tests on residue from distillation test		
Penetration, 25°C, 100 g, 5 s:	100	250
Ductility, 25°C, 5 cm/min, cm:	40	-
Solubility in trichloroethylene, %:	97.5	-