

مشخصات فنی قیر PG 58

Performance Grade Bitumen PG 58

Item	Value						
Performance Grade:	PG 58						
	16	22					
Average 7 day maximum pavement design temperature °C:	<58						
Minimum pavement design temperature °C:	>16	>22					
Original Binder							
Flash point temp, T48, Minimum °C:	230						
Viscosity, T316, maximum 3pas, test temp °C:	135						
Dynamic shear, T 315, G/sin minimum 1.00 kPa, test temp @ 10 rad/s °C:	58						
Rolling Thin Film Oven Residue (T240)							
Mass change maximum percent:	1.00						
Dynamic shear, T 315, G/sin Maximum 2.20 kPa, test temp @ 10 rad/s, °C:	58						
Pressure Aging Vessel (R 28)							
PAV aging temperature °C:	100						
Dynamic shear, T 315: G/sin maximum 5000 kPa, test temp @ 10 rad/s, °C:	25	22					
Creep stiffness, T 313: S, maximum 300 Mpa m-value, minimum 0.300, test temp @ 60s, °C:	-6	-12					
Direct tension, T314: failure strain, minimum 0.300 test temp @ 60s, °C:	-6	-12					
Critical low cracking temp, PP 42: critical cracking temp determined by PP 42, test temp, °C:	-6	-12					

MES