

مشخصات فنی قیر امولسیون دی‌رگیر 1h CSS

Bitumen Emulsion Grade CSS 1h (Slow)

| Item | Min | Max |
|---|----------|-----|
| Test on emulsions | | |
| Viscosity, Saybolt Furol at 25°C SFs: | 20 | 100 |
| Storage stability test, 24-h, %A: | - | 1 |
| Particle charge test: | Positive | |
| Sieve test, %A: | - | 0.1 |
| Cement mixing test, %: | - | 2 |
| Distillation | | |
| Residue, %: | 57 | - |
| Tests on residue from distillation test | | |
| Penetration, 25°C, 100 g, 5 s: | 40 | 90 |
| Ductility, 25°C, 5 cm/min, cm: | 40 | - |
| Solubility in trichloroethylene, %: | 97.5 | - |

AVISA