



صنایع فارس آویسا

مشخصات فنی قیر محلول MC250  
Cutback Bitumen MC250

Item	Min	Max	Test Method
Kinematic Viscosity at 60°C(140°F), mm <sup>2</sup> /s:	250	500	ASTM D2170
Flash Point (Tag Open –cup), °C(°F):	66(150)	-	ASTM D3143
Distillate test : Distillate, volume percent of total distillate to 360 °C (680 °F)			
To 225 °C (437 °F):	-	10	ASTM D402
To 260 °C (500 °F):	15	55	ASTM D402
To 316 °C (600 °F):	60	87	ASTM D402
Tests on residue from distillation :			
Residue from distillation to 360°C(680°F), percent volume by difference:	67	-	ASTM D5
Penetration at 25 °C (77 °F) , 100 gr , 5 s:	120	250	ASTM D113
Ductility at 25°C (77 °F) , cm:	100	-	ASTM D2042
Solubility in trichloroethylene , (% by mass):	99.0	-	AASHTO T 102
Water , (% by volume):	-	0.2	ASTM D95

*Handwritten signature*



صنایع فارس آویسا  
شماره ثبت ۲۷۱۲۲۲

Suit 03, NO.18, Soltani St, Africa Blvd, Tehran, Iran

Tel : +98 21 22034812 , Fax : +98 21 89786897 , Cell : +98 912 6499338